

SECTION 06100
ROUGH CARPENTRY

PART 1 - GENERAL

1.1 RELATED DOCUMENTS

- A. Drawings and general provisions of Contract, including General and Supplementary Conditions and Division 1 Specifications Sections, apply to this section.

1.2 SUMMARY

- A. This section includes the following:
 - 1. Framing with dimension lumber.
 - 2. Wood grounds, nailers, and blocking.
 - 3. Roof Sheathing
- B. Related Sections: The following Sections contain requirements that relate to this Section:
 - 1. Division 6 Section "Finish Carpentry" for nonstructural carpentry items exposed to view and not specified in another Section.

1.3 DEFINITIONS

- A. Rough carpentry includes carpentry work not specified as part of other Sections and generally not exposed, unless otherwise specified.

1.4 SUBMITTALS

- A. General: Submit the following in accordance with Conditions of Contract and Division 1 Specification Sections.
- B. Material certificates for dimensional lumber specified to comply with minimum allowable unit stresses. Indicate species in grade selected for each use as well as design values approved by the Board of Review of American Lumber Standards Committee.
- C. Wood treatment data as follows including chemical treatment, manufacturers instructions for handling, storing, installation, and finishing of treated material:
 - 1. For each type of preservative treated wood product include certification by treating plant stating type of preservative solution and pressure process used, net amount of preservative retained, and compliance with applicable standards.
 - 2. For water-borne treated products include statement that moisture content of treated materials was reduced to levels indicated prior to shipment to project site.

1.5 DELIVERY AND STORAGE

- A. Delivery and Storage: Keep materials under cover and dry. Protect against exposure to weather and contact with damp or wet surfaces. Stack lumber as well as plywood and other panels; provide for air circulation within and around stacks and under temporary coverings including polyethylene and similar materials.

1. For lumber and plywood pressure treated with water-borne chemicals, place spacers between each bundle to provide air circulation.

PART 2 - PRODUCTS

2.1 LUMBER, GENERAL

- A. Lumber Standards: Furnish lumber manufactured to comply with PS 20 "American Softwood Lumber Standard" and with applicable grading rules of inspection agencies certified by American Lumber Standards Committee's (ALSC) Board of Review.
- B. Inspection Agencies: Inspection agencies and the abbreviations used to reference them with lumber grades and species include the following:
 1. SPIB - Southern Pine Inspection Bureau.
 2. WCLIB - West Coast Lumber Inspection Bureau.
- C. Grade Stamps: Provide lumber with each piece factory-marked with grade stamp of inspection agency evidencing compliance with grading rule requirements and identifying grading agency, grade, species, moisture content at time of surfacing, and mill.
- D. Nominal sizes are indicated, except as shown by detail dimensions. Provide actual sizes as required by PS 20, for moisture content specified for each use.
 1. Provide dressed lumber, S4S, unless otherwise indicated.
 2. Provide seasoned lumber with 19 percent maximum moisture content at time of dressing and shipment for sizes 2 inches or less nominal thickness, unless otherwise indicated.
 3. Roof sheathing shall be Exterior Grade Exposure thickness shall be 5/8".

2.2 DIMENSION LUMBER

- A. For light framing (2 to 4 inches thick, 2 to 4 inches wide), provide the following grade and species:
 1. "Standard" grade.
 2. Southern Pine graded under SPIB rules.

2.3 FASTENERS

- A. General: Provide fasteners of size and type indicated that comply with requirements specified in this article for material and manufacture.
 1. Where rough carpentry is exposed to weather, in ground contact, or in area of high relative humidity, provide fasteners with a hot-dip zinc coating per ASTM A 153 or of AISI type 304, stainless steel.
- B. Nails Wire, Brads, and Staples: FS FF-N-105
- C. Power Driven Fasteners: National Evaluation Report NER-272.
- D. Wood Screws: ANSI B18.6.1
- E. Lag Bolts: ANSI B18.2.1
- F. Bolts: Steel bolts complying with ASTM A 307, Grade A; with ASTM A 563 hex nuts and where indicated flat washers.

2.04 MISCELLANEOUS MATERIALS

- A. Water Repellent Preservative: NWWDA tested and accepted formulation containing 3-iodo-2-propenyl butyl carbonate (IPBC) as its active ingredient.

2.05 PRESERVATIVE WOOD TREATMENT BY PRESSURE PROCESS

- A. General: where lumber or plywood is indicated as preservative-treated wood or is specified herein to be treated, comply with applicable requirements of AWPA Current Standards. Mark each treated item with the AWPB or SPIB Quality Mark Requirements.
- B. Pressure-treat above-ground items with water-borne preservatives to a minimum retention of 0.25 pcf. For interior uses, after treatment, kiln-dry lumber and plywood to a maximum moisture content of, respectively, 19 and 15 percent. Treat indicated items and the following:
 - 1. Wood cants, nailers, curbs, equipment support bases, blocking, stripping, and similar members in connection with roofing, flashing, vapor barriers and waterproofing.
 - 2. Wood sills, sleepers, blocking, furring, stripping, and similar concealed members in contact with masonry or concrete.
- C. Complete fabrication of treated items prior to treatment, where possible. If cut after treatment, coat cut surfaces to comply with AWPA M4. Inspect each piece of lumber or plywood after drying and discard damaged or defective pieces.

PART 3 - EXECUTION

3.1 INSTALLATION, GENERAL

- A. Discard units of material with defects that impair quality of rough carpentry construction and that are too small to use in fabricating rough carpentry with minimum joints or optimum joint arrangement.
- B. Set rough carpentry to required levels and lines, with members plumb and true to line and cut and fitted.
- C. Roof Sheathing: Apply roof sheathing to metal deck with screws of type and size recommended by Roofing Material Manufacturer, for his installation.
- D. Fit rough carpentry to other construction; scribe and cope as required for accurate fit.
- E. Countersink nail heads on exposed carpentry work and fill holes.

3.2 WOOD GROUNDS, NAILERS, BLOCKING, AND SLEEPERS

- A. Install wood grounds, nailers, blocking and sleepers where required for attachment of other work. Form to shapes as shown and cut as required for true line and level of work to be attached. Coordinate location with other work involved.
- B. Attach to substrates as required to support applied loading. Countersink bolts and nuts flush with surfaces. Build into masonry during installation of masonry work.

END OF SECTION